

PERFECT COAT CPF - 905

판넬 도막코팅 방수제

PANEL COATING WATERPROOFING

CHEMPROOF

Waterproofing System

● 특징

CPF - 905는 아크릴 에멀전 합성고분자 판넬용 도막방수제로서 실링방수 성능을 갖고 있으며 균열에 대한 내구성이 우수하며 자외선에 의한 변색이 없으며 일반 수성페인트와 결합이 손쉽게 되며 작업 시 은폐력이 좋습니다. 또한 이음새가 없어 완벽한 일체형 도막을 형성합니다.

● 용도

- 샌드위치 판넬, 철 지붕 외 방수를 필요로 하는 부분

● 주의사항

- 반드시 원액을 사용하십시오.
- 제품 보관은 5°C 이상을 유지하고 동결에 주의하십시오.
- 실내에 보관하십시오.
- 어린이의 손에 닿지 않는 곳에 보관하십시오.
- 피부에 묻었을 경우 비눗물로 씻으십시오.
- 5°C 이하에서는 작업을 금하고, 작업시 3~4시간 후 우천일 경우 작업을 하지마십시오.

● 사용방법

1. 피착면의 이물질 유분, 먼지 등을 제거 및 물청소를 시행하고, 바탕면이 충분히 건조된 상태를 확인합니다. 시공면이 부실할 경우 프라이머 (CPF - 100) 을 붓, 롤러, 에어리스 (스프레이) 를 사용하여 도포합니다.
2. 피착 면에 부실한 부위 (피스 및 결합부위) 를 체크하여 실링제 (자사 / PUTTY SEAL) 를 이용하여 보수 또는 보강합니다.
3. 프라이머 도포면이 완전히 경화되었다면 본 제품을 붓, 롤러, 에어리스 (스프레이) 등을 이용하여 도포 작업을 하고 2차 도포는 1차 도포가 완전히 경화된 후 실시합니다. (한번에 2mm이상 두께를 올렸을 경우 표면에 갈라짐 현상이 일어날 수 있음)

● 포장단위 / 색상

- 1.9kg, 18kg Pail / 색상 : 청색, 적갈색, 흑색 외

● 소요량

- PERFECT PRIMER CPF - 100 : 0.3kg/m²
- PERFECT COAT CPF - 905 : 0.8~1kg/m²

● Feature

CPF - 905 is a sealer waterproofing agent for acrylic emulsion synthetic polymer panel. It has sealing waterproofing ability, excellent durability against cracking, has no discoloration due to ultraviolet rays, easy to combine with general water paint, and has excellent hiding power. In addition, there is no joint to form a perfect integral coating film.

● Uses

Sandwich panels, iron roofs and other areas that require waterproofing

● Precautions

- Be sure to use the undiluted solution.
- Keep the product at least 5°C and be careful about freezing.
- Please keep it inside.
- Keep out of reach of children.
- If it gets on your skin, wash it with soapy water.
- Do not work at temperatures below 5°C.
- Do not work if it is raining within 3~4 hours of operation.

● How to use

1. Remove foreign matter, dust, etc. from the adhered surface and clean the water. Check that the substrate is fully dried. If the construction surface is poor, apply primer (V-100) using a brush, roller or airless (spray).
2. Check the poor surface (piece and bonding area) on the surface to be repaired or reinforce using sealant (own putty seal).
3. If the primer coating is completely cured, apply this product using a brush, roller, airless (spray), etc. Second application can start after the first application is fully cured. (If the thickness is increased more than 2mm at a time, the surface may be cracked)

● Packing Unit & Color

- Packing unit : 9kg, 18kg Pail / Color : Blue, Reddish brown, Black, etc.

● Standard Requirements


- PERFECT PRIMER CPF - 100 : 0.3kg/m²
- PERFECT COAT CPF - 905 : 0.8~1kg/m²



GHI



KOYANMAR



* For further information, please refer to Material Safety Data Sheet (MSDS).
* 기타 상세한 자료는 물질안전보건자료 (MSDS)를 참조하십시오.

Supplier in Myanmar



UNIVERSALBIRD TRADING CO., LTD.

Yangon Branch : Room No. 6C, Aye Yeik Thar Condominium, No. (483),
Aye Yeik Thar (2) Street, Bahan Tsp. Yangon, Myanmar

MP : 09-44476-7044 (Myanmar & English)

MP : 09-44476-7045 (Korean & English)



GHI CO., LTD. 16gil - 6 Jinjang Bukgu, Ulsan, Korea

Tel : 82-52-298-2259, Direct MP : 82-10-9300-2259

E-mail : steve@ghi.cc Myanmar MP : 09-42173-9844 (Korean)



Registered ISO 9001, 14001